



**CLEAR  
DEFENSE™ 6**

**EDGE ANTI-GRAFFITI BENEFITS:**

- Protect Against Etching, Acid, Paints, and Markers
- Improve Appearance of Public Spaces
- Removable Sacrificial Film Layer
- Approximately 5%-10% of the Cost of Glass Replacement
- Apply to Many Smooth Surfaces such as Glass, Mirrors, and Stainless Steel

**SPECIFICATIONS**

|                                    |            |
|------------------------------------|------------|
| Visible Light Transmission         | 89%        |
| Visible Light Reflectance (Ext)    | 10%        |
| Visible Light Reflectance (Int)    | 10%        |
| Solar Heat Gain Coefficient (SHGC) | 0.83       |
| Solar Absorption                   | 13%        |
| Total Solar Energy Rejected (TSER) | 17%        |
| UV Rejection                       | >99%       |
| Film Thickness                     | 0.006"     |
| Tensile Strength                   | 25,000 psi |

**CLEAR  
DEFENSE™ 6**



**CLEAR  
DEFENSE™ 4**

**EDGE ANTI-GRAFFITI BENEFITS:**

- Protect Against Etching, Acid, Paints, and Markers
- Improve Appearance of Public Spaces
- Removable Sacrificial Film Layer
- Approximately 5%-10% of the Cost of Glass Replacement
- Apply to Many Smooth Surfaces such as Glass, Mirrors, and Stainless Steel

**SPECIFICATIONS**

|                                    |            |
|------------------------------------|------------|
| Visible Light Transmission         | 89%        |
| Visible Light Reflectance (Ext)    | 9%         |
| Visible Light Reflectance (Int)    | 9%         |
| Solar Heat Gain Coefficient (SHGC) | 0.84       |
| Solar Absorption                   | 10%        |
| Total Solar Energy Rejected (TSER) | 16%        |
| UV Rejection                       | >99%       |
| Film Thickness                     | 0.004"     |
| Tensile Strength                   | 25,000 psi |

**CLEAR  
DEFENSE™ 4**